

Product Information



Monocal® GP Grease (1499-1498)

**Versatile Grease with Calcium Sulfonate Complex Thickener
Protects Equipment from Heat, Moisture & Heavy Loads**

Lubrication Engineers, Inc. formulated Monocal® GP Grease for use in environments with challenging conditions such as high temperatures, heavy loads and the presence of water. Its high-performance formula features high-viscosity base fluid, calcium sulfonate complex thickener and Monolec®, LE's proprietary wear-reducing additive. Available in NLGI 2 and 1 grades, this premium combination imparts a very high dropping point, exceptional inherent extreme pressure (EP) characteristics, superior mechanical stability, low oil bleed, and water resistance – everything you need to protect and extend the life of your equipment.



A versatile general purpose lubricant, Monocal GP Grease is the right solution for industrial and mobile equipment used in a wide variety of industries. It is especially effective when used on bearings operating in a warm, moist environment or in operations where a lot of water is needed to keep equipment cool. Without effective, reliable lubrication, these conditions can lead to costly downtime and repairs.

Beneficial Qualities

High-performance formula

- Performs effectively in severe conditions such as heat, water and heavy loads
- Provides long-lasting reliable protection
- Ensures very low oil separation
- Features high-viscosity base fluid (ISO 220)

Calcium sulfonate thickener

- Inherently prevents rust and corrosion – even in sea water
- Has very high dropping point as compared to conventional thickeners
- Ensures excellent mechanical stability for long-lasting use

- Imparts outstanding EP properties (without the addition of heavy metals), providing protection even when pound-out conditions occur

Wear-reducing additive

- Protects against wear, metal-to-metal contact and scoring
- Provides exceptional film strength
- Resists oxidation and water contamination
- Maintains consistency after repeated heating and cooling

Available Grades

- NLGI 2 (1499)
- NLGI 1 (1498)

Proprietary Additive

LE's proprietary additives are used exclusively in LE lubricants. Monocal® GP Grease contains Monolec.

Monolec® wear-reducing additive creates a single molecular lubricating film on metal surfaces, vastly increasing oil film strength without affecting clearances. An invaluable component in LE's engine oils, industrial oils and many of its other lubricants, Monolec allows opposing surfaces to slide by one another, greatly reducing friction, heat and wear.



Asset Reliability Solutions™

www.le-bv.nl
T: +31 (0)78 - 654 99 66



Technical Data

Monocal® GP Grease

Performance Requirements Met or Exceeded

- USDA H2

Recommendations

- Can be used in Diamond Power soot blowers
- Can be used in anti-friction bearings up to 6,000 rpm

Typical Industries

- Agriculture
- Chemicals
- Construction
- Lumber & wood
- Mining
- Oil & gas
- Paper products
- Power generation
- Refuse & waste systems
- Rubber & plastic
- Steel & primary metals
- Transportation & fleet
- Water & wastewater
- Any industries where hot weather, humidity and overheated machinery create moisture problems

Typical Applications

- Industrial: Bearings (anti-friction, conveyor, fan, heavily loaded ball, high-speed, plain, roller element, slow-speed), forging equipment, machine tools, presses, rolling mills and rotary aerators
- Automotive: Ball joints, chassis, front axle arrangements, U-joints, wheel bearings

Thickener Type

Texture

Color

NLGI Grade

Worked 60 Penetration ASTM D217

Worked 10K Penetration ASTM D217

Worked 100K Penetration ASTM D217

Dropping Point °C (°F), ASTM D2265

Base Fluid Characteristics

Flash Point °C (°F), ASTM D92

Viscosity @ 40°C, cSt, ASTM D445

Oxidation drop in psi @ 100 hrs, ASTM D942

Oxidation drop in psi @ 500 hrs, ASTM D942

Corrosion Prevention DI H₂O, ASTM D1743

Corrosion Prevention 5% Sea H₂O, ASTM D5969

Timken OK Load lbs, ASTM D2509

Four-Ball EP Weld Point kgf, ASTM D2596

Four-Ball EP Load Wear Index kgf, ASTM D2596

Four-Ball Wear @ 75°C, 1,200 rpm, 40 kgf 60 minutes, mm wear, ASTM D2266

Water Spray-off % loss, ASTM D4049

Copper Corrosion 24 hrs @ 100°C, ASTM D4048

Evaporation 22 hrs @ 100°C, % loss, ASTM D972

1499

Calcium Sulfonate
Complex

Smooth

Blue

2

280

±5%

±7%

316 (600)

>260 (>500)

220

≤5

≤8

Pass

Pass

60

400

50.0

0.50

<20.0

1b

<2.0

1498

Calcium Sulfonate
Complex

Smooth

Blue

1

325

±5%

±7%

316 (600)

>260 (>500)

220

≤5

≤8

Pass

Pass

60

400

50.0

0.50

-

1b

<2.0



Monocal® and Monolec® are registered trademarks of Lubrication Engineers, Inc.

LI30117 11-13, rev. 11-17

Jacobus Lipsweg 100 - NL-3316 BP Dodrecht - info@le-bv.nl
LE operates under an ISO 9001 Certified Quality System.

www.le-bv.nl
T: +31 (0)78 - 654 99 66