

Grease Compatibility Chart

	Aluminum Complex	Calcium	Calcium 12-Hydroxy	Calcium Complex	Clay Inorganic (Bentone)	Lithium	Lithium 12-Hydroxy	Lithium Complex	Polyurea	Calcium Sulfonate Complex
Aluminum Complex		No	No	No	No	No	No	Yes	No	No
Calcium	No		Yes	No	No	Yes	Borderline	Yes	No	Yes
Calcium 12-Hydroxy	No	Yes		Borderline	No	Yes	Yes	Yes	No	Yes
Calcium Complex	No	No	Borderline		No	No	No	Yes	Yes	Yes
Clay Inorganic (Bentone)	No	No	No	No		No	No	No	No	No
Lithium	No	Yes	Yes	No	No		Yes	Yes	No	Yes
Lithium 12-Hydroxy	No	Borderline	Yes	No	No	Yes		Yes	No	Yes
Lithium Complex	Yes	Yes	Yes	Yes	No	Yes	Yes		Borderline	Yes
Polyurea	No	No	No	Yes	No	No	No	Borderline		No
Calcium Sulfonate Complex	No	Yes	Yes	Yes	No	Yes	Yes	Yes	No	
 LE Greases Domestic	1274/1275 1295/1297 1298/1299 3353* 4022/4023 4024/4025 4700/4701/4702	451*/452* 453*			1250/1251 4051 5180/5182 9901		1232	3750/3751 3752 4622	1282	1487/1488 1498/1499 4070/4071 4072

*Coating Grease

This chart is for reference only; it is intended as a starting point to determine whether two greases might be compatible. Additional testing might be warranted.